


# DUAL ISOLATED THIN FILM NETWORKS

## MSIR 3 SERIES

The MSIR series dual isolated chip resistor offers greater flexibility for the hybrid designer seeking resistor pairs with excellent T.C.R./T.C. tracking between resistors.



NOTCHED PAD INDICATES LOCATION OF R1

### MECHANICAL DATA

SIZE	0.030" x 0.030" x 0.010" ( $\pm 0.003$ ")
SUBSTRATE	SILICON, ALUMINA, QUARTZ, OR GLASS
RESISTOR	NICHROME OR TANTALUM NITRIDE
BOND PADS	15K $\Omega$ MINIMUM GOLD STANDARD; ALUMINUM AVAILABLE
BACKSIDE SURFACE	BARE SUBSTRATE; GOLD BACK OPTIONAL

### ELECTRICAL DATA

RESISTANCE RANGE	VALUES FROM 1 $\Omega$ TO 1M $\Omega$ PER SIDE; CONSULT SALES FOR SPECIFIC COMBINATIONS OR FOR HIGHER VALUES
TOLERANCES	0.01%, 0.02%, 0.05%, 0.1%, 0.25%, 0.5%, 1%, 2%, 5%, 10%
RESISTANCE RATIO	$\pm 1\%$ STD.; AVAIL. TO $\pm 0.01\%$
T.C.R.	NICHROME: $\pm 50$ ppm STD.; $\pm 25$ ppm, $\pm 10$ ppm, $\pm 5$ ppm OPTIONAL TANTALUM NITRIDE: $\pm 100$ ppm STD.; $\pm 50$ ppm, $\pm 25$ ppm, $\pm 10$ ppm OPTIONAL TO $\pm 2$ ppm/ $^{\circ}$ C; VALUE DEPENDENT
T.C. TRACKING	

### SERIES DATA

CURRENT NOISE	-20dB TYPICAL
DIELECTRIC BREAKDOWN	400 V MIN.
INSULATION RESISTANCE	10 <sup>12</sup> $\Omega$ MIN.
OPERATING VOLTAGE	100 V MAX.
POWER RATING	
SILICON & ALUMINA	250 mW TOTAL (70 $^{\circ}$ C DERATED LINEARLY TO 150 $^{\circ}$ C). P = E <sup>2</sup> /R
QUARTZ & GLASS	50 mW TOTAL (70 $^{\circ}$ C DERATED LINEARLY TO 150 $^{\circ}$ C). P = E <sup>2</sup> /R
SHORT TERM OVERLOAD	5X RATED POWER, 25 $^{\circ}$ C, 5 SEC., $\pm 0.25\%$ MAX. $\Delta$ R/R: 0.1% MSI TYPICAL
HIGH TEMP EXPOSURE	150 $^{\circ}$ C, 100 HRS., $\pm 0.25\%$ MAX. $\Delta$ R/R: 0.03% MSI TYPICAL
THERMAL SHOCK	MIL-STD 202, METHOD 107F, $\pm 0.25\%$ MAX. $\Delta$ R/R: 0.1% MSI TYPICAL
MOISTURE RESISTANCE	MIL-STD 202, METHOD 106, $\pm 0.5\%$ MAX. $\Delta$ R/R: 0.1% MSI TYPICAL
STABILITY	1000 HRS., 70 $^{\circ}$ C, 125mW, $\pm 0.5\%$ MAX. $\Delta$ R/R: 0.1% MSI TYPICAL
OPERATING TEMP RANGE	-55 $^{\circ}$ C TO +125 $^{\circ}$ C
STABILITY RATIO	0.1% MAX. $\Delta$ R/R STANDARD: 0.05% MAX. $\Delta$ R/R OPTIONAL
FREQUENCY	TO 20 GHz (RESISTOR GEOMETRY DEPENDENT)
STRAY DISTRIBUTED CAPACITANCE	
SILICON / NiCr OR TaN	2pF
ALUMINA / NiCr	0.06pF
ALUMINA / TaN	0.08pF
QUARTZ / NiCr	0.02pF
QUARTZ / TaN	0.05pF
GLASS / NiCr	0.04pF
GLASS / TaN	0.06pF

### PART NUMBER DESIGNATION

MSIR 3	X	X	XXXXX / XXXXX	X / X	X
SERIES	SUBSTRATE	RESISTIVE FILM	OHMIC CODES R1 / R2	TOLERANCE CODES	OPTION DESIGNATOR (If Required)
	A = Alumina G = Glass Q = Quartz S = Silicon	N = Nichrome T = Tantalum Nitride	5-Digit Number: 1st 4 Digits Are Significant With "R" As Decimal Point When required. 5th Digit Represents Number of Zeros. R1 $\leq$ R2 300R0F/500R0F 25000B/10001B	S = 0.01% X = 0.02% Q = 0.05% B = 0.1% C = 0.25% D = 0.5% F = 1% G = 2% J = 5% K = 10%	A = $\pm 50$ ppm/ $^{\circ}$ C B = $\pm 25$ ppm/ $^{\circ}$ C C = $\pm 10$ ppm/ $^{\circ}$ C D = $\pm 5$ ppm/ $^{\circ}$ C E = Aluminum Bond Pads F = $\pm 100$ ppm/ $^{\circ}$ C **G = Gold Bond Pads GB = Gold Backside RB = 0.05% RATIO RC = 0.1% RATIO RD = 0.5% RATIO **Std. if no other option required.



45 FRANK MOSSBERG DRIVE, ATTLEBORO, MA 02703  
508-226-2111 FAX: 508-226-2211

EXAMPLES: MSIR 3ST-300R0B/500R0B-A = Silicon/Tantalum Nitride with  
R1 = 300 $\Omega$ ,  $\pm 0.1\%$ , R2 = 500 $\Omega$ ,  $\pm 0.1\%$  Tol.,  $\pm 50$ ppm/ $^{\circ}$ C T.C.R., with Gold Bond Pads

\* PART MARKING AVAILABLE, CONSULT SALES.